

Thionation of NDI molecules as a revolutionary approach to photovoltaic properties

Hamid Reza Shamlouei^{✉1}, Nurullah Khurshidvand^{✉2} and Reza Safari^{✉3}

1. Corresponding author, Department of Chemistry, University of Lorestan, Khorramabad, Iran. Email: shamlouei.ha@lu.ac.ir
2. Corresponding author, Department of Chemistry, Faculty of Sciences, Islamic Azad University of Arak, Arak, Iran. Email: khurshidvand.chemistry@gmail.com
3. Department of Chemistry, Faculty of Science, University of Qom, Qom, Iran.

Article Info

Article type:

Research Article

Article history:

Received 24 Jun 2024

Received in revised form 16 Aug 2024

Accepted 22 Oct 2024

Published online 25 Dec 2024

Keywords:

Photovoltaic properties, Organic solar cells, Donor-Acceptor-Donor molecule, NDI molecule, Fill factor.

ABSTRACT

This work introduces the effect of thionation using density functional theory (DFT) and time-dependent density functional theory (TD-DFT) on the photovoltaic properties of naphthalene diimide-carbazole molecule for application in organic solar cells. According to the obtained results, the optical, electronic, and photovoltaic properties after thionation were significantly improved compared to the virgin molecule. The results of calculations of dipole moment, polarizability, and hyperpolarizability showed that thionation significantly increases the charge density distribution. The open circuit voltage of each of the studied structures was calculated with the PC61BM receiver, and the results showed an improvement in performance after thionation. The value of the open circuit voltage for the naphthalene diimide-carbazole molecule was 1.54 V, which increased to 1.61 V after thionation. Finally, high values of fill factor and light harvesting efficiency predict significant power conversion efficiency after thionation. These outcomes position our modified molecule as a promising candidate for advancing organic solar cell technology, offering a pathway toward more efficient and effective photovoltaic devices.

Cite this article: Shamlouei, H. & et al, (2024). Thionation of NDI molecules as a revolutionary approach to photovoltaic properties, *Advances in Energy and Materials Research*, 1 (4), 18-27. <https://doi.org/10.22091/jaem.2025.10922.1014>

© The Author(s).

DOI: 10.22091/jaem.2025.10922.1014

Publisher: University of Qom.

1. Introduction

In recent years, the quest for efficient and sustainable energy sources has intensified, driving significant advancements in photovoltaic technology [1-5]. Among the innovative strategies emerging to enhance solar cell efficiency is the integration of NDI (naphthalene diimide) molecules as acceptors within the design of donor-acceptor-donor (D-A-D) architectures [6,7]. NDI molecules, known for their strong electron-accepting nature and excellent stability, represent a pivotal advancement in the realm of organic photovoltaics [8, 9]. By strategically positioning NDI units as the central acceptor in D-A-D architectures, researchers capitalize on their ability to efficiently capture and transport electrons generated upon photon absorption [10-12]. This design not only enhances the overall photovoltaic efficiency but also addresses challenges such as material stability and cost-effectiveness, crucial for large-scale deployment [13, 14]. Moreover, the tunability of NDI structures allows for precise modification of their electronic properties, tailoring them to specific energy levels required for optimal charge separation and extraction [15,16]. This flexibility opens avenues for engineering D-A-D systems with finely tuned absorption spectra and improved compatibility with complementary donor materials, thereby maximizing light harvesting across broader solar spectrum ranges [17-22]. In the pursuit of advancing organic photovoltaics (OPVs), researchers have increasingly focused on modifying the chemical structure of naphthalene diimide (NDI) molecules through strategic substitutions of atoms and functional groups [23-26]. This systematic approach aims to enhance the photovoltaic properties of NDIs by tailoring their electronic structure, energy levels, and intermolecular interactions within donor-acceptor-donor systems [27, 28]. This strategy improves the power conversion efficiency in OPVs [29, 30]. In the realm of organic photovoltaics (OPVs), the quest for materials with enhanced performance characteristics has led researchers to explore innovative chemical modifications. One such transformative approach gaining significant attention is thionation - the substitution of oxygen atoms with sulfur in organic molecules [31-34]. This strategic modification holds immense promise for improving the photovoltaic properties of materials by altering their electronic structure, energy levels, and intermolecular interactions [35, 36]. The thionation of naphthalene diamide (NDI) molecules as acceptors in donor-acceptor-donor (D-A-D) architectures can promise the emergence of materials with improved photovoltaic properties. This transformative approach not only aims to bolster the efficiency and stability of OPVs but also addresses critical challenges such as broader absorption spectra and reduced energy losses [37, 38]. In this regard, this

paper addresses the strategic importance of the thionation effect on the NDI molecule in OPVs specifically designed to increase photovoltaic performance.




Figure 1. Donor and acceptor parts in this study.

2. Computational method

Bulk heterojunction solar cells are typically composed of a mixture of π -conjugated electron donor material and a fullerene derivative as the electron acceptor material: (6,6)-Phenyl-C61 Butyric Acid Methyl Ester (PC61BM) [39-41]. For this purpose, each of the studied structures (NDI-Carbazole, NDI-S-Carbazole, and PC61BM) was drawn using the GaussView program. Then, to achieve the best molecular geometry, the structure of each of the studied molecules was optimized using Gaussian 09 software, using density functional theory (DFT) and at the theoretical level of CAM-B3LYP/6-311G+(d,p) [42-46]. Frequency calculations were also performed at the same theoretical level, and no imaginary frequencies were observed. Also, the UV absorption spectrum was calculated using the TD-DFT approach and at the CAM-B3LYP/6-311G+(d,p) theoretical level.

The energy gap ($E_{\text{Gap}} = |E_{\text{HOMO}} - E_{\text{LUMO}}|$) was calculated to investigate the mode of electron transfer between the acceptor and donor parts of the designed structures. E_{HOMO} refers to the energy level of the highest occupied molecular orbital (HOMO), while E_{LUMO} denotes the energy level of the lowest unoccupied molecular orbital (LUMO) [47-49].

Additionally, the chemical potential (μ), and chemical hardness (η) were calculated using equations 1-2, which involve the HOMO and LUMO energy values [50-52].

$$\eta = (-E_{\text{HOMO}} + E_{\text{LUMO}})/2 \quad (1)$$

$$S = \frac{1}{2\eta} \quad (2)$$

The fill factor (FF) in solar cells is crucial as it indicates how effectively the cell converts sunlight into usable electricity. A higher fill factor means more efficient energy conversion, maximizing the power output of the solar cell [53, 54]. The fill factor was calculated using equation 3 for each of the studied structures.

$$FF = \frac{\frac{eV_{oc}}{K_B T} - \ln\left(\frac{eV_{oc}}{K_B T} + 0.72\right)}{\frac{eV_{oc}}{K_B T} + 1} \quad (3)$$

In the above equation, $\frac{eV_{oc}}{K_B T}$ shows normalized Voc, e denotes charge, which is kept at unity in this work. K_B is used to abbreviate the Boltzmann constant, equal to $8.61733034 \times 10^{-5}$ electron volts Kelvin⁻¹ [55, 56].

One of the critical parameters in the field of photovoltaics is the maximum open-circuit voltage (Voc). It is theoretically calculated as the difference between the E_{HOMO} of the electron donor and the E_{LUMO} of the electron acceptor. The value of Voc was calculated in terms of V units based on Eq. 4 [57, 58].

$$Voc = \frac{1}{e} (|E(H_D)| - |E(L_A)|) - 0.3 \quad (4)$$

Where, e , $E(H_D)$ and $E(L_A)$ are the elementary charge on the molecule (its value is kept at 1), HOMO of donor and LUMO of acceptor, respectively.

The light-harvesting efficiency (LHE) is an essential property in solar cells and plays a key role in increasing η . The LHE parameter is related to the oscillator strength (f).

$$LHE = 1 - 10^{-f} \quad (7)$$

f represents the oscillator strength in the complex, which corresponds to the λ_{max} [59].

efficiency and photovoltaic performance of the device [64, 65]. The energy values of HOMO/LUMO orbitals, energy gap (HLG), chemical hardness (η) and chemical softness (S) for each of structures NDI-Carbazole (A) and NDI-S-Carbazole (B) (donor) and PC61BM (acceptor) are reported in Table 1.

Table 1. Energy values of HOMO/LUMO frontier orbitals, energy gap, chemical hardness (η), and chemical softness (S) in each of the studied structures (all values are in eV).

Structure	LUMO	HOMO	HLG	η	S
A	-3.79	-5.84	2.05	1.02	0.49
B	-4.47	-5.91	1.44	0.72	0.69
PC61BM	-4.00	-6.23	2.83	2.83	0.17

Also, for the A structure, energy gap values of 2.05 eV and 1.44 eV for the B structure were obtained. The results show that tuning reduces the energy gap significantly. The results obtained for chemical hardness (A (1.025 eV) > B (0.72 eV)) and chemical softness (B (0.69 eV) > A (0.49 eV)) show that thionation reduces the chemical hardness and thus the molecule becomes more reactive. The increase in chemical softness due to thionation improves the ability of the molecule to transfer charge and increases the efficiency of solar cells.

Also, the frontier molecular orbitals (FMO) for all studied structures are shown in Figure 3. In each of the designed structures (A, B, C, and D-structure), the LUMO orbitals are focused on the acceptor parts (A), and the HOMO orbitals are focused on the donor parts (D) (Figure 2).

3. Results and Discussion

3.1. Electronic prosperity

Studying the HOMO (Highest Occupied Molecular Orbital) and LUMO (Lowest Unoccupied Molecular Orbital) orbitals is essential to grasp the electronic configuration of a molecule and its involvement in diverse phenomena such as electron transfer, chemical reactions, and applications in optoelectronics such as solar cells. The energy levels and relative positions of these orbitals determine the ability of a molecule to donate or accept electrons and affect its photovoltaic properties [60-63].

Also, studies show that the energy levels of frontier orbitals are related (HOMO/LUMO) to chemical hardness and chemical softness. Optimizing these parameters improves efficient charge transfer and exciton separation, which is effective in increasing the




Figure 2. DOS and frontier molecular orbitals (FMO) diagrams for all studied structures.

3.2. Dipole moment (μ), Polarizability (α) and Hyperpolarizability (β)

In the design of donor-acceptor-donor (D-A-D) molecules for use in solar cells, increasing the dipole moment, polarizability and hyperpolarizability can provide several advantages:

1- Enhanced charge separation: Higher polarizability allows more charge separation by absorbing light. When a photon is absorbed, it produces an exciton (an electron-hole pair), and the higher polarizability facilitates the separation of these charges, leading to more efficient charge transport within the device [66, 67].

2- Enhanced exciton dissociation: Hyperpolarizability refers to the nonlinear optical property that governs the efficiency of second harmonic generation (SHG) and two-photon absorption (TPA). In the context of solar cells, higher hyperpolarizability means that more photons can be absorbed to generate excitons, thus improving the dissociation of excitons into free charge carriers [68, 69].

3- Expanded Absorption Range: Larger dipole moments broaden the absorption spectrum, allowing the molecule to absorb a wider range of solar radiation, thereby maximizing energy harvesting potential [70-72].

The polarizability (α) and first hyperpolarizability (β), corresponding to linear and NLO properties, were calculated using Eqs. 8-10 [73, 74].

$$\alpha = 1/3(\alpha_{xx} + \alpha_{yy} + \alpha_{zz}) \quad (8)$$

$$\beta^0 = (\beta_x^2 + \beta_y^2 + \beta_z^2)^{1/2} \quad (9)$$

In which

$$\beta_i = 3/5(\beta_{iii} + \beta_{ijj} + \beta_{ikk}) \quad i, j, k=x, y, z \quad (10)$$

The obtained values for dipole moment, polarizability and hyperpolarizability are reported in Table 2.

Table 2. Values of dipole moment (μ), polarizability (α) and hyperpolarizability (β) for the structures investigated in this work.

Structure	μ	α	β
A	3.18	21.34	156.12
B	4.52	28.39	175.34

After thionation, the dipole moment increased from 3.18 to 4.52. Polarizability values for A and B structures were obtained as 21.34 and 28.39, respectively. The hyperpolarizability was calculated for structure A to be 156.12 and for structure B to be 175.34. These results show that thionation significantly affects the values of dipole moment, polarizability, and hyperpolarizability and causes each of them. It seems that thionation causes more charge separation between atoms and thereby increases the dipole moment. This increase in polarizability increases the molecule's ability to interact with electric fields, thereby increasing its hyperpolarizability.

MEP analysis provides valuable insight into the three-dimensional distribution of molecular charges and the determination of sites susceptible to electrophilic and nucleophilic attacks (Figure 3). Electrophiles tend to target regions of high charge density, usually shown in yellow and red, while blue regions represent regions of relatively lower charge density and serve as potential sites for interactions. They act as nucleophiles. Neutral regions within the molecule are usually shown in green. The greater the width between the red and blue colors, the greater the dipole moment of the molecule and, as a result, the charge distribution [75-77].




Figure 3. MEP maps for designed molecules (A-structure and B-structure).

Figure 5 shows the MEP map of the electron density distribution in each of the studied structures from the donor to the acceptor parts. In structures A and B, the blue color is retained by the central part of the molecule. It is also clear that the areas with yellow and red are concentrated in the donor sector. This feature indicates the successful transfer of charge from the donor to the acceptor units and shows that the phenomenon of intramolecular charge transfer (CT) from the donor to the acceptor has occurred in both structures.

3.3. Optical properties

Table 3 and Figure 4 show the results of maximum absorption wavelengths (λ_{max}), oscillator strength (f), excitation energies (E_{ex}) and HOMO to LUMO assignments for each of the studied structures. The values of λ_{max} for each of the investigated structures were calculated as follows: for structure A, λ_{max} =670 nm; for the B-structure, λ_{max} =1029 nm was calculated (Figure 6). The obtained results show that the

substitution of sulfur instead of oxygen in the NDI molecule extends the absorption wavelength to longer wavelengths. The reason for this can be related to the increase in electron density and decrease in the HOMO-LUMO energy gap after thionation, which facilitates the transfer of charge from the donor to the acceptor in the molecule.

Consequently, the absorption spectrum shifts to longer wavelengths, enabling the capture of a broader range of solar radiation and enhancing the overall efficiency of the solar cell.




Figure 4. The UV spectrum of the designed structures using the method TD/DFT/CAM-B3LYP/6-311+G(d,p).

Table 3. The calculated values of the optical parameters; maximum absorption wavelengths (λ_{max}), oscillator strength (f), excitation energies (E_{ex}) and HOMO to LUMO assignments.

Structure	λ_{max} (nm)	E_{ex} (eV)	f	Assignment
A	670	1.8501	0.0011	HOMO→LUMO (98%)
B	1029	1.2043	0.0156	HOMO→LUMO (99%)

The value of E_{ex} as an important indicator provides us with useful information about the process of electron excitation from the conduction band (LUMO) to the valence band (HOMO) [96, 97]. A lower E_{ex} value indicates easier electron excitation [98,

99]. Table 3 shows Eex values for each of the studied structures. Eex values for each of the A and B structures were obtained as 1.8501 eV and 1.2043 eV, respectively. Structure B has a lower Eex value (1.2043 eV) that facilitates electron transfer in the donor-acceptor complex.

According to the obtained results, the change in exciton energy values is directly correlated with the change in the energy gap, as excitons are bound states of an electron and a hole, formed due to the energy difference between the conduction and valence bands.

3.4. Open circuit voltage (Voc), fill factor (FF) and Light harvesting efficiency (LHE)

In the design of D-A-D solar cells, the measurements of open circuit voltage (Voc) and fill factor (FF) are essential, as they play an important role in efficiency optimization. Voc provides insights into charge segregation in structures, while FF shows how charges are efficiently transported and collected in the cell [78-81]. These parameters are effective in designing new structures and maximizing the power conversion efficiency and the overall performance of the solar cell. Also, Light harvesting efficiency (LHE) represents the ability of the cell to absorb and convert incident light into electrical energy, which is influenced by factors such as absorption spectrum matching and charge carrier mobility. Maximizing light harvesting efficiency increases the power conversion efficiency of the cell, making it more effective at converting sunlight into usable electricity [82-84]. For this purpose, Voc, FF, and LHE values were calculated for each of the structures and the findings were reported in Table 4.

Table 4. Values of open circuit voltage (Voc) fill factor (FF), and Light harvesting efficiency (LHE) for the investigated structures.

Structure	circuit voltage (Voc)	fill factor (FF)	LHE
A	1.54	0.82	0.002
B	1.61	0.96	0.035

The values of Voc for each of the A and B structures were calculated to be 1.54 V and 1.61 V, respectively. Also, the FF values were calculated for the structure of A, 0.82, and the structure of B, 0.96. As the results show, the values obtained for Voc and FF improved after thionation, which can be due to the improvement of charge transfer properties in the molecule. Higher Voc indicates better energy conversion efficiency as more of the absorbed sunlight is converted into electrical potential without significant losses. This directly increases the overall efficiency of the solar cell. Increasing FF means reducing losses due to resistive effects within the cell. It signifies improved charge carrier collection and reduced recombination losses, leading to higher output power from the solar cell. These developments are very important to increase the overall efficiency and performance of organic solar cells. Also, the values obtained for LHE in each of the studied structures (structure A=0.002 and structure

B=0.035) show that thionation is a suitable solution to improve and increase LHE values. Solar cells convert sunlight into electricity, and higher light-harvesting efficiency means more photons are converted into electrical current. This directly increases the power output of the solar cell for a given surface area, which is crucial for improving the overall efficiency of solar energy systems.

4. Conclusion

In this study, the effect of thionation on the electronic and photovoltaic properties of the naphthalene diimide-carbazole molecule was investigated. In this regard, the structure of the pristine molecule (structure A) and thionated molecule (structure B) were optimized through DFT and TD-DFT methods using CAM-B3LYP/6-311+G(d,p) theoretical level. The energy gap values, chemical hardness, and chemical softness were calculated as 2.05 eV, 1.02 eV, and 0.49 eV for structure A and 1.44 eV, 0.72 eV, and 0.69 eV, respectively, for structure B. These results show that thionation significantly reduced the energy gap and affected the reactivity of the molecule. Dipole moment, Polarizability, and Hyperpolarizability increased due to thionation. Also, after thionation, the absorption wavelength increased from 670 nm to 1029 nm. The values of FF, Voc, and LHE for structure A were calculated as 1.54, 0.82, and 0.002, respectively and for structure B as 1.61, 0.96, and 0.035, respectively. Evaluation of FF, Voc, and LHE after thionation showed that the modified molecule (structure B) can have higher efficiency than molecule A. In the end, the findings of this study showed that thionation, the process of substituting sulfur-containing groups instead of oxygen, can be used as a promising strategy in increasing the photovoltaic properties of materials used in solar cell technology.

Conflict of Interest

No potential conflict of interest was reported by the authors.

Funding

There is no funding for this manuscript.

Acknowledgment

There is no acknowledgment for this manuscript.

Reference

- [1] Sathe, T. M., & Dhoble, A. S. (2017). A review on recent advancements in photovoltaic thermal techniques. *Renewable and Sustainable Energy Reviews*, 76, 645-672. DOI: <https://doi.org/10.1016/j.rser.2017.03.075>

- [2] Guillén-López, A., Delesma, C., Amador-Bedolla, C., Robles, M. and Muñiz, J., 2018. Electronic structure and nonlinear optical properties of organic photovoltaic systems with potential applications on solar cell devices: a DFT approach. *Theoretical Chemistry Accounts*, 137(6), p.85. DOI: <https://doi.org/10.1007/s00214-018-2267-3>
- [3] Li, Y., Huang, X., Sheriff Jr, H.K. and Forrest, S.R., 2023. Semitransparent organic photovoltaics for building-integrated photovoltaic applications. *Nature Reviews Materials*, 8(3), pp.186-201. DOI: <https://doi.org/10.1038/s41578-022-00514-0>
- [4] Pandey, S. V., Ganapuram, S., & Singh, A. K. (2021). A review on advancements in photovoltaic cells. *Advances in Interdisciplinary Engineering: Select Proceedings of FLAME 2020*, 227-236. DOI: https://doi.org/10.1007/978-981-15-9956-9_23
- [5] Dada, M. and Popoola, P., 2023. Recent advances in solar photovoltaic materials and systems for energy storage applications: a review. *Beni-Suef University Journal of Basic and Applied Sciences*, 12(1), pp.1-15. DOI: <https://doi.org/10.1186/s43088-023-00405-5>
- [6] Rybakiewicz, R., Ganczarczyk, R., Charyton, M., Skorka, L., Ledwon, P., Nowakowski, R., & Pron, A. (2020). Low band gap donor-acceptor-donor compounds containing carbazole and naphthalene diimide units: Synthesis, electropolymerization and spectroelectrochemical behaviour. *Electrochimica Acta*, 358, 136922. DOI: <https://doi.org/10.1016/j.electacta.2020.136922>
- [7] Lasitha, P. (2020). Radical anion formation exhibiting “turn-on” fluorescence sensing of hydrazine using a naphthalene diimide (NDI) derivative with a donor-acceptor-donor (DAD) molecular structure. *Photochemical & Photobiological Sciences*, 19(11), 1603-1612. DOI: <https://doi.org/10.1039/D0PP00232A>
- [8] Avinash, M. B., Swathi, K., Narayan, K. S., & Govindaraju, T. (2016). Molecular architectonics of naphthalenediimides for efficient structure–property correlation. *ACS Applied Materials & Interfaces*, 8(13), 8678-8685. DOI: <https://doi.org/10.1021/acsami.6b00011>
- [9] Zhou, N., & Facchetti, A. (2018). Naphthalenediimide (NDI) polymers for all-polymer photovoltaics. *Materials Today*, 21(4), 377-390. DOI: <https://doi.org/10.1016/j.mattod.2018.02.003>
- [10] Al Kobaisi, M., Bhosale, S. V., Latham, K., Raynor, A. M., & Bhosale, S. V. (2016). Functional naphthalene diimides: synthesis, properties, and applications. *Chemical reviews*, 116(19), 11685-11796. DOI: <https://doi.org/10.1021/acs.chemrev.6b00160>
- [11] Royakkers, J., Guo, K., Toolan, D. T., Feng, L. W., Minotto, A., Congrave, D. G., & Bronstein, H. (2021). Molecular Encapsulation of Naphthalene Diimide (NDI) Based π -Conjugated Polymers: A Tool for Understanding Photoluminescence. *Angewandte Chemie International Edition*, 60(47), 25005-25012. DOI: <https://doi.org/10.1002/anie.202110139>
- [12] Fernando, R., Mao, Z., Muller, E., Ruan, F., & Sauvé, G. (2014). Tuning the organic solar cell performance of acceptor 2, 6-dialkylaminonaphthalene diimides by varying a linker between the imide nitrogen and a thiophene group. *The Journal of Physical Chemistry C*, 118(7), 3433-3442. DOI: <https://doi.org/10.1021/jp411432a>
- [13] Yang, J., Xiao, B., Tang, A., Li, J., Wang, X., & Zhou, E. (2019). Aromatic - diimide - based n -type conjugated polymers for all - polymer solar cell applications. *Advanced Materials*, 31(45), 1804699. DOI: <https://doi.org/10.1002/adma.201804699>
- [14] Sung, M. J., Huang, M., Moon, S. H., Lee, T. H., Park, S. Y., Kim, J. Y., & Kim, Y. H. (2017). Naphthalene diimide-based small molecule acceptors for fullerene-free organic solar cells. *Solar Energy*, 150, 90-95. DOI: <https://doi.org/10.1039/C7TA02749D>
- [15] Liu, W., Shaikh, D. B., Rao, P. S., Bhosale, R. S., Said, A. A., Mak, A. M., & Zhang, Q. (2020). Molecular aggregation of naphthalene diimide (NDI) derivatives in electron transport layers of inverted perovskite solar cells and their influence on the device performance. *Chemistry—An Asian Journal*, 15(1), 112-121.
- [16] Jameel, M. A., Yang, T. C. J., Wilson, G. J., Evans, R. A., Gupta, A., & Langford, S. J. (2021). Naphthalene diimide-based electron transport materials for perovskite solar cells. *Journal of Materials Chemistry A*, 9(48), 27170-27192. DOI: <https://doi.org/10.1002/asia.201901452>
- [17] Chung, H. Y., Oh, J., Park, J. H., Cho, I., Yoon, W. S., Kwon, J. E., & Park, S. Y. (2020). Spectroscopic studies on intramolecular charge-transfer characteristics in small-molecule organic solar cell donors: a case study on ADA and DAD triad donors. *The Journal of Physical Chemistry C*, 124(34), 18502-18512. DOI: <https://doi.org/10.1021/acs.jpcc.0c06741>
- [18] Leliege, A., Blanchard, P., Rousseau, T., & Roncali, J. (2011). Triphenylamine/tetracyanobutadiene-based DAD π -conjugated systems as molecular donors for organic solar cells. *Organic Letters*, 13(12), 3098-3101. DOI: <https://doi.org/10.1021/ol201002j>
- [19] Wei, Q., Liu, W., Leclerc, M., Yuan, J., Chen, H., & Zou, Y. (2020). A-DA' DA non-fullerene acceptors for high-performance organic solar cells. *Science China Chemistry*, 63, 1352-1366. DOI: <https://doi.org/10.1007/s11426-020-9799-4>
- [20] Lai, H., Chen, H., Zhu, Y., Chen, L., Huang, H. H., & He, F. (2020). An asymmetrical A-DAD-A-type acceptor simultaneously enhances voltage and current for efficient organic solar cells. *Journal of materials chemistry A*, 8(19), 9670-9676. DOI: <https://doi.org/10.1039/D0TA03128C>
- [21] Feng, H., Qiu, N., Wang, X., Wang, Y., Kan, B., Wan, X., Zhang, M., Xia, A., Li, C., Liu, F. and Zhang, H., 2017. An ADA type small-molecule electron acceptor with end-extended conjugation for high performance organic solar cells. *Chemistry of Materials*, 29(18), pp.7908-7917. DOI: <https://doi.org/10.1021/acs.chemmater.7b02811>
- [22] Shang, H., Fan, H., Shi, Q., Li, S., Li, Y., & Zhan, X. (2010). Solution processable DAD molecules based on triphenylamine for efficient organic solar cells. *Solar Energy Materials and Solar Cells*, 94(3), 457-464.
- [23] Suraru, S. L., & Würthner, F. (2014). Strategies for the synthesis of functional naphthalene diimides. *Angewandte Chemie International Edition*, 53(29),

- 7428-7448. DOI: <https://doi.org/10.1002/anie.201309746>
- [24] Bhosale, S. V., Al Kobaisi, M., Jadhav, R. W., Morajkar, P. P., Jones, L. A., & George, S. (2021). Naphthalene diimides: perspectives and promise. *Chemical Society Reviews*, 50(17), 9845-9998. DOI: <https://doi.org/10.1039/D0CS00239A>
- [25] Das, A., & Ghosh, S. (2016). H-bonding directed programmed supramolecular assembly of naphthalene-diimide (NDI) derivatives. *Chemical communications*, 52(42), 6860-6872. DOI: <https://doi.org/10.1039/C6CC01983H>
- [26] Insuasty, A., Maniam, S., & Langford, S. J. (2019). Recent advances in the core - annulation of naphthalene diimides. *Chemistry-A European Journal*, 25(29), 7058-7073. DOI: <https://doi.org/10.1002/chem.201806009>
- [27] Yang, J., Xiao, B., Tajima, K., Nakano, M., Takimiya, K., Tang, A., & Zhou, E. (2017). Comparison among perylene diimide (PDI), naphthalene diimide (NDI), and naphthodithiophene diimide (NDTI) based n-type polymers for all-polymer solar cells application. *Macromolecules*, 50(8), 3179-3185. DOI: <https://doi.org/10.1021/acs.macromol.7b00414>
- [28] Cassinelli, M., Cimò, S., Biskup, T., Jiao, X., Luzio, A., McNeill, C. R., & Caironi, M. (2021). Enhanced N - Type Doping of a Naphthalene Diimide Based Copolymer by Modification of the Donor Unit. *Advanced Electronic Materials*, 7(12), 2100407. DOI: <https://doi.org/10.1002/aelml.202100407>
- [29] Yang, J., Chen, F., Xiao, B., Sun, S., Sun, X., Tajima, K., & Zhou, E. (2018). Modulating the Symmetry of Benzodithiophene by Molecular Tailoring for the Application in Naphthalene Diimide - Based N - Type Photovoltaic Polymers. *Solar RRL*, 2(4), 1700230. DOI: <https://doi.org/10.1002/solr.201700230>
- [30] Ali, U., Javed, A., Ramzan, H., Shoaib, M., Raza, A., Khalil, M.T., Cheng, S.B. and Iqbal, J., 2020. Molecular designing of naphthalene diimide based fullerene-free small organic solar cell-Acceptors with high photovoltaic performance by density functional theory. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 228, p.117685. Ortiz-Rodríguez, L. A., & Crespo-Hernández, C. E. (2020). Thionated organic compounds as emerging heavy-atom-free photodynamic therapy agents. *Chemical Science*, 11(41), 11113-11123. DOI: <https://doi.org/10.1016/j.saa.2019.117685>
- [31] Kaleta, Z., Makowski, B. T., Soós, T., & Dembinski, R. (2006). Thionation using fluoros Lawesson's reagent. *Organic Letters*, 8(8), 1625-1628. DOI: <https://doi.org/10.1021/ol060208a>
- [32] Legnani, L., Toma, L., Caramella, P., Chiacchio, M. A., Giofre, S., Delso, I., & Merino, P. (2016). Computational mechanistic study of thionation of carbonyl compounds with Lawesson's reagent. *The Journal of organic chemistry*, 81(17), 7733-7740. DOI: <https://doi.org/10.1021/acs.joc.6b01420>
- [33] Pahlavanlu, P., Tilley, A. J., McAllister, B. T., & Seferos, D. S. (2017). Microwave synthesis of thionated naphthalene diimide-based small molecules and polymers. *The Journal of Organic Chemistry*, 82(23), 12337-12345. DOI: <https://doi.org/10.1021/acs.joc.7b02162>
- [34] Zhang, H., Liu, M., Yang, W., Judin, L., Hukka, T. I., Priimagi, A., & Vivo, P. (2019). Thionation enhances the performance of polymeric dopant - free hole - transporting materials for perovskite solar cells. *Advanced Materials Interfaces*, 6(18), 1901036. DOI: <https://doi.org/10.1002/admi.201901036>
- [35] Rundel, K., Shin, Y. H., Chesman, A. S., Liu, A. C., Welford, A., Thomsen, L., ... & McNeill, C. R. (2019). Effect of thionation on the performance of PNDIT2-based polymer solar cells. *The Journal of Physical Chemistry C*, 123(19), 12062-12072. DOI: <https://doi.org/10.1021/acs.jpcc.8b11935>
- [36] Chen, W., Nakano, M., Takimiya, K., & Zhang, Q. (2017). Selective thionation of naphthal [2, 3-b] thiophene diimide: tuning of the optoelectronic properties and packing structure. *Organic Chemistry Frontiers*, 4(5), 704-710. DOI: <https://doi.org/10.1039/C6QO00871B>
- [37] Welford, A., Maniam, S., Gann, E., Thomsen, L., Langford, S. J., & McNeill, C. R. (2018). Thionation of naphthalene diimide molecules: Thin-film microstructure and transistor performance. *Organic Electronics*, 53, 287-295. DOI: <https://doi.org/10.1016/j.orgel.2017.11.038>
- [38] Heeger, A. J. (2014). 25th anniversary article: bulk heterojunction solar cells: understanding the mechanism of operation. *Advanced materials*, 26(1), 10-28. DOI: <https://doi.org/10.1002/adma.201304373>
- [39] Huang, Y., Kramer, E. J., Heeger, A. J., & Bazan, G. C. (2014). Bulk heterojunction solar cells: morphology and performance relationships. *Chemical reviews*, 114(14), 7006-7043. DOI: <https://doi.org/10.1021/cr400353v>
- [40] Park, S. H., Roy, A., Beaupré, S., Cho, S., Coates, N., Moon, J. S., & Heeger, A. J. (2009). Bulk heterojunction solar cells with internal quantum efficiency approaching 100%. *Nature photonics*, 3(5), 297-302. Bagayoko, D. (2014). Understanding density functional theory (DFT) and completing it in practice. *AIP Advances*, 4(12). DOI: <https://doi.org/10.1038/nphoton.2009.69>
- [41] Bagayoko, D. (2014). Understanding density functional theory (DFT) and completing it in practice. *AIP Advances*, 4(12). DOI: DOI: <https://doi.org/10.1063/1.4903408>
- [42] Obot, I. B., Macdonald, D. D., & Gasem, Z. M. (2015). Density functional theory (DFT) as a powerful tool for designing new organic corrosion inhibitors. Part 1: an overview. *Corrosion Science*, 99, 1-30. DOI: <https://doi.org/10.1016/j.corsci.2015.01.037>
- [43] Yanai, T., Tew, D. P., & Handy, N. C. (2004). A new hybrid exchange-correlation functional using the Coulomb-attenuating method (CAM-B3LYP). *Chemical physics letters*, 393(1-3), 51-57. DOI: <https://doi.org/10.1016/j.cplett.2004.06.011>
- [44] Li, M., Reimers, J. R., Ford, M. J., Kobayashi, R., & Amos, R. D. (2021). Accurate prediction of the properties of materials using the CAM - B3LYP density functional. *Journal of Computational Chemistry*, 42(21), 1486-1497. DOI: <https://doi.org/10.1002/jcc.26558>

- [45] Hilal, I.H., Jabbar, R.H. and Jabbar, S.J., 2021, April. Structural properties of aluminum doped with zinc oxide (ZnO) nanoparticle theoretical study by Gaussian 09 program. In IOP Conference Series: Earth and Environmental Science (Vol. 722, No. 1, p. 012027). IOP Publishing. DOI: <https://doi.org/10.1088/1755-1315/722/1/012027>
- [46] Sham, L. J., & Schlüter, M. (1983). Density-functional theory of the energy gap. *Physical review letters*, 51(20), 1888. DOI: [https://doi.org/10.1016/S0065-3276\(08\)60593-6](https://doi.org/10.1016/S0065-3276(08)60593-6)
- [47] Ravindra, N. M., Ganapathy, P., & Choi, J. (2007). Energy gap–refractive index relations in semiconductors—An overview. *Infrared physics & technology*, 50(1), 21-29. DOI: <https://doi.org/10.1016/j.infrared.2006.04.001>
- [48] Varshni, Y. P. (1967). Temperature dependence of the energy gap in semiconductors. *physica*, 34(1), 149-154.
- [49] Franco-Pérez, M., Gázquez, J. L., Ayers, P. W., & Vela, A. (2015). Revisiting the definition of the electronic chemical potential, chemical hardness, and softness at finite temperatures. *The Journal of chemical physics*, 143(15). DOI: <https://doi.org/10.1063/1.4932539>
- [50] Pearson, R. G. (2005). Chemical hardness and density functional theory. *Journal of Chemical Sciences*, 117, 369-377. DOI: <https://doi.org/10.1007/BF02708340>
- [51] Shankar, R., Senthilkumar, K., & Kolaival, P. (2009). Calculation of ionization potential and chemical hardness: a comparative study of different methods. *International Journal of Quantum Chemistry*, 109(4), 764-771. DOI: <https://doi.org/10.1002/qua.21883>
- [52] Janjua, M. R. S. A. (2022). All-small-molecule organic solar cells with high fill factor and enhanced open-circuit voltage with 18.25% PCE: Physical insights from quantum chemical calculations. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 279, 121487. DOI: <https://doi.org/10.1016/j.saa.2022.121487>
- [53] Gao, W., Liu, T., Zhong, C., Zhang, G., Zhang, Y., Ming, R., & Yang, C. (2018). Asymmetrical small molecule acceptor enabling nonfullerene polymer solar cell with fill factor approaching 79%. *ACS Energy Letters*, 3(7), 1760-1768. DOI: <https://doi.org/10.1021/acsenenergylett.8b00825>
- [54] Janjua, M. R. S. A. (2023). Impact of symmetry breaking on the performance of non-fullerene acceptors (NFAs) for photo and thermally stable organic solar cells (OSCs): a DFT-based interrogation and investigation. *Journal of Photochemistry and Photobiology A: Chemistry*, 444, 115003. DOI: <https://doi.org/10.1016/j.jphotochem.2023.115003>
- [55] Khan, M. U., Shafiq, F., Janjua, M. R. S. A., Khalid, M., Yaqoob, J., Arshad, M., & Khan, R. A. (2024). Predicting benzodithiophene based donor materials with enhanced 19.09% PCE, open-circuit voltage and optoelectronic attributes for solar cell applications: Photochemical insights from DFT. *Journal of Photochemistry and Photobiology A: Chemistry*, 446, 115115. DOI: <https://doi.org/10.1016/j.jphotochem.2023.115115>
- [56] Xiao, M., Tian, Y., & Zheng, S. (2018). An insight into the relationship between morphology and open circuit voltage/electronic absorption spectrum at donor-acceptor interface in boron subphthalocyanine chloride/C70 solar cell: A DFT/TDDFT exploration. *Organic Electronics*, 59, 279-287. DOI: <https://doi.org/10.1016/j.orgel.2018.05.021>
- [57] Khan, M. U., Shafiq, F., Janjua, M. R. S. A., Khalid, M., Yaqoob, J., Arshad, M., & Khan, R. A. (2024). Predicting benzodithiophene based donor materials with enhanced 19.09% PCE, open-circuit voltage and optoelectronic attributes for solar cell applications: Photochemical insights from DFT. *Journal of Photochemistry and Photobiology A: Chemistry*, 446, 115115. DOI: <https://doi.org/10.1016/j.jphotochem.2023.115115>
- [58] Raftani, M., Abram, T., Bennani, N., & Bouachrine, M. (2020). Theoretical study of new conjugated compounds with a low bandgap for bulk heterojunction solar cells: DFT and TD-DFT study. *Results in Chemistry*, 2, 100040. DOI: <https://doi.org/10.1016/j.rechem.2020.100040>
- [59] Zhang, G., & Musgrave, C. B. (2007). Comparison of DFT methods for molecular orbital eigenvalue calculations. *The journal of physical chemistry A*, 111(8), 1554-1561. DOI: <https://doi.org/10.1021/jp061633o>
- [60] Pereira, F., Xiao, K., Latino, D. A., Wu, C., Zhang, Q., & Aires-de-Sousa, J. (2017). Machine learning methods to predict density functional theory B3LYP energies of HOMO and LUMO orbitals. *Journal of chemical information and modeling*, 57(1), 11-21. DOI: <https://doi.org/10.1021/acs.jcim.6b00340>
- [61] Choudhary, V., Bhatt, A., Dash, D., & Sharma, N. (2019). DFT calculations on molecular structures, HOMO–LUMO study, reactivity descriptors and spectral analyses of newly synthesized diorganotin (IV) 2 - chloridophenylacetohydroxamate complexes. *Journal of computational chemistry*, 40(27), 2354-2363. DOI: <https://doi.org/10.1002/jcc.26012>
- [62] Huang, Y., Rong, C., Zhang, R., & Liu, S. (2017). Evaluating frontier orbital energy and HOMO/LUMO gap with descriptors from density functional reactivity theory. *Journal of molecular modeling*, 23, 1-12. DOI: <https://doi.org/10.1007/s00894-016-3175-x>
- [63] Kim, B. G., Ma, X., Chen, C., Ie, Y., Coir, E. W., Hashemi, H., & Kim, J. (2013). Energy level modulation of HOMO, LUMO, and band - gap in conjugated polymers for organic photovoltaic applications. *Advanced Functional Materials*, 23(4), 439-445. DOI: <https://doi.org/10.1002/adfm.201201385>
- [64] Yang, H., Cui, C., & Li, Y. (2021). Effects of heteroatom substitution on the photovoltaic performance of donor materials in organic solar cells. *Accounts of Materials Research*, 2(11), 986-997. DOI: <https://doi.org/10.1021/accountsmr.1c00119>
- [65] Xu, T., Lu, L., Zheng, T., Szarko, J. M., Schneider, A., Chen, L. X., & Yu, L. (2014). Tuning the polarizability in donor polymers with a thiophenesaccharin unit for organic photovoltaic applications. *Advanced Functional Materials*, 24(22), 3432-3437. DOI: <https://doi.org/10.1002/adfm.201303688>

- [66] Li, M., Qin, Y., Dai, W., & Luo, X. (2018). Tuning the performance of the non-fullerene organic solar cells by the polarizability. *RSC advances*, 8(7), 3809-3815. DOI: <https://doi.org/10.1039/C7RA11297A>
- [67] Zhang, Z., Li, L., Xu, C., Jin, P., Huang, M., Li, Y., & Lin, Y. (2022). Single photovoltaic material solar cells with enhanced exciton dissociation and extended electron diffusion. *Cell Reports Physical Science*, 3(6). DOI: <https://doi.org/10.1016/j.xcrp.2022.100895>
- [68] Aïssa, B., Ali, A., Bentouaf, A., Khan, W., Zakaria, Y., Mahmoud, K. A., & Mansour, S. A. (2019). Influence of single-walled carbon nanotubes induced exciton dissociation improvement on hybrid organic photovoltaic devices. *Journal of Applied Physics*, 126(11). DOI: <https://doi.org/10.1063/1.5105388>
- [69] Carsten, B., Szarko, J. M., Son, H. J., Wang, W., Lu, L., He, F., & Yu, L. (2011). Examining the effect of the dipole moment on charge separation in donor-acceptor polymers for organic photovoltaic applications. *Journal of the American Chemical Society*, 133(50), 20468-20475. DOI: <https://doi.org/10.1021/ja208642b>
- [70] Privado, M., de la Cruz, P., Malhotra, P., Sharma, G. D., & Langa, F. (2021). Influence of the dipole moment on the photovoltaic performance of polymer solar cells employing non-fullerene small molecule acceptor. *Solar Energy*, 221, 393-401. DOI: <https://doi.org/10.1016/j.solener.2021.04.049>
- [71] Ji, X., Wang, T., Fu, Q., Liu, D., Wu, Z., Zhang, M., & Liu, Y. (2023). Deciphering the Effects of Molecular Dipole Moments on the Photovoltaic Performance of Organic Solar Cells. *Macromolecular Rapid Communications*, 44(23), 2300213. DOI: <https://doi.org/10.1002/marc.202300213>
- [72] Kamada, K., Ueda, M., Nagao, H., Tawa, K., Sugino, T., Shmizu, Y., & Ohta, K. (2000). Molecular design for organic nonlinear optics: polarizability and hyperpolarizabilities of furan homologues investigated by ab initio molecular orbital method. *The Journal of Physical Chemistry A*, 104(20), 4723-4734. DOI: <https://doi.org/10.1021/jp993806v>
- [73] Kumar, S., Surbhi, & Yadav, M. K. (2021). Optimized Molecular Geometries, Internal Coordinates, Vibrational Analysis, Thermodynamic Properties, First Hyperpolarizability and HOMO-LUMO Analysis of Duroquinone Using Density Functional Theory and Hartree-Fock Method. *Russian Journal of Physical Chemistry B*, 15, S22-S31. DOI: <https://doi.org/10.1134/S1990793121090116>
- [74] Uludağ, N., & Serdaroğlu, G. (2018). An improved synthesis, spectroscopic (FT-IR, NMR) study and DFT computational analysis (IR, NMR, UV-Vis, MEP diagrams, NBO, NLO, FMO) of the 1, 5-methanoazocino [4, 3-b] indole core structure. *Journal of Molecular Structure*, 1155, 548-560. DOI: <https://doi.org/10.1016/j.molstruc.2017.11.032>
- [75] Ramalingam, S., Karabacak, M., Periandy, S., Puvvarasan, N., & Tanuja, D. (2012). Spectroscopic (infrared, Raman, UV and NMR) analysis, Gaussian hybrid computational investigation (MEP maps/HOMO and LUMO) on cyclohexanone oxime. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, 96, 207-220. DOI: <https://doi.org/10.1016/j.saa.2012.03.090>
- [76] Saral, A., Sudha, P., Muthu, S., Sevvanthi, S., & Irfan, A. (2022). Molecular structure spectroscopic Elucidation, IEFPCM solvation (UV-Vis, MEP, FMO, NBO, NLO), molecular docking and biological assessment studies of lepidine (4-Methylquinoline). *Journal of Molecular Liquids*, 345, 118249. DOI: <https://doi.org/10.1016/j.molliq.2021.118249>
- [77] Lee, J. K., & Yang, M. (2011). Progress in light harvesting and charge injection of dye-sensitized solar cells. *Materials Science and Engineering: B*, 176(15), 1142-1160. DOI: <https://doi.org/10.1016/j.mseb.2011.06.018>
- [78] Ogunsolu, O.O., Wang, J.C. and Hanson, K., 2017. Increasing the open-circuit voltage of dye-sensitized solar cells via metal-ion coordination. *Inorganic Chemistry*, 56(18), pp.11168-11175. DOI: <https://doi.org/10.1021/acs.inorgchem.7b01531>
- [79] Koide, N., Islam, A., Chiba, Y., & Han, L. (2006). Improvement of efficiency of dye-sensitized solar cells based on analysis of equivalent circuit. *Journal of Photochemistry and Photobiology A: chemistry*, 182(3), 296-305. DOI: <https://doi.org/10.1016/j.jphotochem.2006.04.030>
- [80] Gao, X. D., Li, X. M., & Gan, X. Y. (2013). Enhancing the light harvesting capacity of the photoanode films in dye-sensitized solar cells. *Intechopen Europe*, 169-202. DOI: <https://doi.org/10.1016/j.optmat.2023.114074>
- [81] Aboy, M., Pelaz, L., López, P., Marqués, L. A., Duffy, R., & Venezia, V. C. (2006). Physical insight into boron activation and redistribution during annealing after low-temperature solid phase epitaxial regrowth. *Applied physics letters*, 88(19). DOI: <https://doi.org/10.1063/1.2203334>
- [82] Tachibana, Y., Hara, K., Sayama, K., & Arakawa, H. (2002). Quantitative analysis of light-harvesting efficiency and electron-transfer yield in ruthenium-dye-sensitized nanocrystalline TiO₂ solar cells. *Chemistry of Materials*, 14(6), 2527-2535. DOI: <https://doi.org/10.1021/cm011563s>
- [83] Hosseini, Z., Diau, E. W. G., Mehrany, K., & Taghavinia, N. (2014). Assessment of Luminescent Downshifting Layers for the Improvement of Light - Harvesting Efficiency in Dye - Sensitized Solar Cells. *ChemPhysChem*, 15(17), 3791-3799. DOI: <https://doi.org/10.1002/cphc.201402505>